

10643610 01/07/94



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : D04H 13/00	A1	(11) International Publication Number: WO 94/11557 (43) International Publication Date: 26 May 1994 (26.05.94)
<p>(21) International Application Number: PCT/US93/10437</p> <p>(22) International Filing Date: 5 November 1993 (05.11.93)</p> <p>(30) Priority data: 07/973,876 10 November 1992 (10.11.92) US</p> <p>(71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).</p> <p>(72) Inventors: LIM, Hyun, Sung ; 5303 Copperpenny Court, Chesterfield, VA 23832 (US). PETERSON, Robert, Howe ; 102 Blue Ridge Trace, Hendersonville, TN 37075-2538 (US). SIEMIONKO, Roger, Keith ; 36 Stonebridge Drive, Hockessin, DE 19707-9184 (US). VINCENT, James, Ralph ; 208 Rising Sun Lane, Old Hickory, TN 37138 (US).</p>		<p>(74) Agents: SCHAEFFER, Andrew, L. et al.; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).</p> <p>(81) Designated States: CA, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published With international search report.</p>
<p>(54) Title: HYDROENTANGLED FLASH SPUN WEBS HAVING CONTROLLABLE BULK AND PERMEABILITY</p> <p>(57) Abstract</p> <p>A process for hydraulically needling a web of stapled fibers into an unbonded flash spun web made of continuous plexifilaments to form a spunlaced nonwoven fabric. The web of staple fibers is positioned against the unbonded flash spun web and then hydraulically needled such that the staple fibers are embedded into and entangled with the unbonded flash spun web to form a spunlaced nonwoven fabric. Optionally, the spunlaced nonwoven fabric can be thermally bonded to maintain or increase the permeability of the fabric. Thermal bonding can be used to control the level of permeability depending on the end-use desired. Spunlaced nonwoven fabrics made by the inventive process are particularly useful in filtration applications (e.g., vacuum cleaner bags) when thermal bonding is employed and as bulky, downproof and featherproof barrier liners for garments, sleeping bags, pillows, comforters and the like when thermal bonding is not employed.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LJ	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TC	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

TITLE

Hydroentangled Flash Spun Webs Having
Controllable Bulk and Permeability

FIELD OF THE INVENTION

5 The present invention relates to a process for
hydroentangling a web of staple fibers with an unbonded
flash spun web made of continuous plexifilaments to form a
composite nonwoven fabric. In particular, the present
10 invention relates to hydraulically needling staple fibers
into an unbonded flash spun nonwoven web such that the
staple fibers are embedded into and entangled with the
unbonded flash spun nonwoven web.

BACKGROUND OF THE INVENTION

15 Spunbonded sheets of flash-spun polyolefin
plexifilamentary film-fibril strands have been used in the
past as disposable industrial garments. Such sheets have
been made commercially by E. I. du Pont de Nemours &
Company and sold under the trademark "TYVEK" spunbonded
20 olefin. The sheets are known for their strength,
durability, opacity and ability to act as a barrier to
particulate matter that is sub-micron in size. Because of
these desirable characteristics, the spunbonded sheets have
been fashioned into many types of industrial garments, such
as those worn by asbestos workers and disclosed in
25 "Protective Apparel of Du Pont "TYVEK" - SAFETY YOU CAN
WEAR", E-02145, (1987).

 Although these sheets are useful in garment and
apparel applications, there has been a need to add
30 bulkiness and permeability to the sheets so that they are
also useful in other specific end-use applications (e.g.,
as microfiltration fabrics). Although unconsolidated flash
spun sheets have fairly high permeability in the unfused
state, it is lost when the sheet is thermally bonded since
fusing reduces permeability to a level that is unsuitable
35 for sensitive filtration applications (e.g., vacuum cleaner
bags). This is attributed to high mechanical consolidation
of the microdenier, ribbon-like, high surface area fibers

produced by the flash spinning process. Because of the limited ability of the flash spinning and thermal bonding process to increase permeability beyond a Gurley-Hill porosity of about 8 second/100cc, there is a significant need for a method to be developed which will increase or even maintain the permeability to a Frazier porosity of at least 4 ft³/ft²/min following thermal bonding.

Various methods have been suggested in the past for providing filtration media from sheets made of flash spun plexifilaments. An example of such filtration media is commercially available from E. I. du Pont de Nemours and Company under the trademark "HYSURF" filter media. However, these methods (e.g., U.S. Patent 5,047,121 (Kochar)) require numerous process steps and equipment for cutting up and refining the flash spun sheets into pulp suitable for wet-laying on continuous papermaking machines. Only if these steps are carefully followed will subsequent thermal bonding produce a high grade paper suitable for microfiltration applications (e.g., vacuum cleaner bags).

In addition, in U.S. Patent 5,023,130 (Simpson et al.) hydroentangled flash spun polyolefin webs are disclosed having enhanced softness and barrier properties. Spunlaced fabrics made according to the Simpson et al. process are commercially available from E. I. du Pont de Nemours and Company under the trademarks "TYPRO HC" and "ComforMax IB". These spunlaced fabrics have proven useful as inner-layer barrier liners for garments, sleeping bags, comforters and pillows. However, although these spunlaced fabrics work well with fiber insulating or filling materials, they do not work well in preventing percolation when duck feathers or down filling are used. Experience has shown that feather quills migrate through available openings in the fabric.

Moreover, in U.S. Patent 4,681,801 (Eian et al.) melt-blown fiber webs are hydroentangled to force reinforcing fibers therethrough. The reinforcing fibers are hydraulically needled, preferably mechanically needled, through the melt-blown fibers and then bonded to fibers on

the opposing faces of the layer of melt-blown fibers to hold the reinforcing fibers in position.

Clearly, what is needed is a process and spunlaced
5 nonwoven fabric which do not have the deficiencies inherent in the prior art. In particular, in the unfused state, the spunlaced fabric should have bulk and should prevent percolation of feathers or down filling when used as a barrier liner in garments, pillows or the like. In
10 addition, in the thermally bonded state, the spunlaced fabric should provide an increased level of permeability such that it is useful in sensitive microfiltration applications. Other objects and advantages of the present invention will become apparent to those skilled in the art
15 upon reference to the attached drawings and to the detailed description of the invention which hereinafter follows.

SUMMARY OF THE INVENTION

In one aspect of the invention, there is provided a process for making a spunlaced nonwoven fabric comprising
20 the steps of:

(a) positioning a web of staple fibers against an unbonded flash spun web on a supporting screen to form a composite structure; and

(b) hydraulically needling the staple fiber side
25 of the supported composite structure such that the staple fibers penetrate the unbonded flash spun web and are embedded into and entangled with the unbonded flash spun web.

This process produces unfused, spunlaced nonwoven
30 fabrics having a Frazier porosity of at least 4 $\text{ft}^3/\text{ft}^2/\text{min}$. These unfused spunlaced fabrics are particularly well suited as inner-layer barrier fabrics such as liners for pillows, sleeping bags, comforters and disposable industrial garments (e.g., protective and
35 medical barrier apparel). Because the pores of the unbonded flash spun web have been sufficiently closed by the penetration of stiff staple fibers into the unbonded flash spun web structure, feathers and down filling cannot

percolate through the fabric itself (i.e., the fabric is downproof and featherproof). Presently, this advantage is only possible when expensive, tightly woven fabrics are used.

In another aspect of the invention, the process further comprises the step of thermally bonding (i.e., fusing) the hydraulically needled fabric of step (b) to maintain or increase the permeability of the resultant fabric depending on the end-use desired. This process surprisingly produces thermally bonded, spunlaced nonwoven fabrics that have a Frazier porosity of at least 4 $\text{ft}^3/\text{ft}^2/\text{min}$, preferably 10-40 $\text{ft}^3/\text{ft}^2/\text{min}$, most preferably 10-20 $\text{ft}^3/\text{ft}^2/\text{min}$. In the prior art, thermal bonding causes spunlaced flash spun webs to suffer a significant decrease in permeability. Because the permeability of the spunlaced fabric can be increased after thermal bonding, the resulting thermally bonded spunlaced fabrics have adequate permeability for many sensitive microfiltration applications (e.g., vacuum cleaner bags) which were not possible in the past. These thermally bonded spunlaced fabrics are also believed to be useful as reinforcement construction materials. The reason for the increase in permeability is believed to be that the stiff staple fibers that are embedded into the unbonded flash spun web of step (b) reduce mechanical consolidation and that the flash spun fibers shrink causing permeability to increase directly with the thermal bonding temperature.

A further advantage of the thermally bonded, spunlaced nonwoven fabric is that the side of the fabric from which the staple fibers penetrate the unbonded flash spun web provide a gradient, depth-type filter that prevents blinding of the microfiber portion of the fabric when in use.

BRIEF DESCRIPTION OF THE DRAWINGS

The invention will be better understood with reference to the following figures:

Fig. 1 is a schematic side view of an apparatus for

continuously forming a composite web structure from staple fibers and an unbonded flash spun web and hydraulically needling the composite web structure to form spunlaced nonwoven fabrics in accordance with the invention.

Fig. 2 is a modified version of Fig. 1 showing belt water jets in addition to drum water jets.

Fig. 3 is a schematic view of a palmer bonder used to optionally thermally bond the spunlaced nonwoven fabric of Figs. 1 or 2.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

One of the starting materials for the process of the present invention is a lightly consolidated or unconsolidated flash-spun polyolefin, preferably polyethylene or polypropylene, plexifilamentary film-fibril web produced by the general procedure of Steuber, U.S. Patent 3,169,899, the entire contents of which are incorporated herein by reference. According to the preferred method for making the starting sheets, a linear polyethylene having a density of 0.96 g/cm^3 , a melt index of 0.9 (determined by ASTM method D-1238-57T, condition E) and a 135 C upper limit of its melting temperature range is flash spun from a 12 weight percent solution of the polyethylene in trichlorofluoromethane. The solution is continuously pumped to spinneret assemblies at a temperature of about 179 C and a pressure above about 85 atmospheres. The solution is passed in each spinneret assembly through a first orifice to a pressure let-down zone and then through a second orifice into the surrounding atmosphere. The resulting film fibril strand (i.e., plexifilament) is spread and oscillated by means of a shaped rotating baffle, electrostatically charged, and then is deposited on a moving collection belt. The spinnerets are spaced to provide overlapping, intersecting deposits on the belt to form a wide, flash spun nonwoven web. The web may then be lightly consolidated by passage through a nip that applies a load of about 1.8 kilograms per cm of web width or it may remain unconsolidated. Generally, webs having a basis

weight in the range of 1.0 to 3.5 oz/yd² are suitable for use in the process of the present invention. Also, webs having a strand diameter of between 1-10 microns are preferred. The web is not thermally bonded or fused (i.e., unbonded) prior to hydraulic needling treatment, the description of which follows hereinafter.

The other starting material is a web of staple fibers. The web may be prepared according to the teachings of U.S. Patent 3,485,706 (Evans), the entire contents of which are incorporated herein by reference. Preferably, the web of staple fibers should be carded or air-laid such that it can easily be positioned against the unbonded flash spun web and supported on a screen (e.g., a 75 mesh screen).

As used herein, "staple fibers" means any relatively stiff staple length fiber that is typically used in the art of hydraulic needling. The fiber must have adequate modulus (i.e., not too high and not too low) to be embedded and entangled with the unbonded flash spun web. The staple fibers can be made of synthetic or natural fibers or blends of both. They may be single component as well as bicomponent staple fibers. Non-limiting examples of suitable staple fibers include those made of woodpulp, polyester, nylon, acrylics and aramids such as "KEVLAR" and "NOMEX".

As used herein, the terms "unfused" or "unbonded" mean that the web or fabric has not been thermally bonded or thermally fused. This is to be distinguished from mechanical bonding (e.g., hydraulic needling or light consolidation).

In use, the web of staple fibers is positioned against an unbonded flash spun web on a supporting screen to form a composite web structure. The basis weight ratio of the staple fiber web to the unbonded flash spun web can be varied depending on the end-use desired. For example, if increased bulkiness is desired, increased amounts of staple fibers are used. The supported composite web structure is then passed under a series of high pressure water jets

(preferably from 200 to 3,000 psi jet pressure) such that the staple fibers are forced (i.e., hydraulically needled) into the unbonded flash spun web. The staple fibers
5 penetrate the flash spun web such that they embed and entangle with the flash spun web and form a spunlaced nonwoven fabric. Methods and equipment suitable for hydraulically needling the composite web structure are disclosed in more detail in the Evans patent and in U.S.
10 Patent 3,403,862 (Dworjanyn). Typically, after the composite web structure is hydraulically needled into a spunlaced nonwoven fabric excess water is removed by vacuum dewatering and/or by squeeze rolls. (Squeeze rolling is a compaction force which causes the spunlaced nonwoven fabric
15 to decrease in permeability). Drying is then performed at a temperature which doesn't cause thermal bonding (i.e., fusing) of the fabric to take place.

Following hydraulic needling, the unbonded, spunlaced nonwoven fabric has added thickness and a Frazier porosity
20 of at least $4 \text{ ft}^3/\text{ft}^2/\text{min}$. The fabric is useful as a bulky, inner-layer barrier fabric for garments, sleeping bags, pillows, comforters and the like. It is also useful as a medical barrier fabric and as a protective apparel. Because the pores of the unbonded flash spun web have been
25 sufficiently blocked by the stiff staple fibers (i.e., increased barrier properties), the resulting spunlaced nonwoven fabric has surprisingly proven to prevent percolation when used with down filling or natural feathers (i.e., quills are prevented from migrating through the
30 fabric).

Optionally, if sensitive filtration or other applications are desired, the spunlaced nonwoven fabric may be thermally bonded. In the past, thermal bonding always caused the permeability of a flash spun web to
35 significantly decrease, just the opposite of what is wanted for microfiltration end-uses. However, to the applicants surprise, thermal bonding actually allows the permeability to be maintained and more importantly increased. In fact,

depending on the level of thermal bonding used, the permeability of the spunlaced nonwoven fabric can be tailored for the desired end-use (this is typically between about 10 and 40 ft³/ft²/min.). This phenomenon is believed to be caused by fiber shrinkage of the flash spun web and because the staple fibers reduce compaction of the flash spun fibers onto themselves during thermal bonding. (Thermal bonding allows fiber shrinkage forces to dominate compaction forces (e.g., squeeze roller compaction)). As a result, the greater the thermal bonding level (i.e., higher the thermal bonding temperature and/or pressure) the greater the permeability is increased. If too low a thermal bonding temperature/pressure is used (i.e., below about 135 C and 48 psi), the permeability will actually be decreased since the compaction forces are greater than resulting fiber shrinkage. Because permeability can be controlled, the resulting thermally bonded, spunlaced nonwoven fabrics typically have a lower pressure drop than synthetic fabrics made on conventional wet-lay papermaking machines (e.g., the high grade polyethylene paper of U.S. Patent 5,047,121 (Kochar)).

It has also been found that varying the amount of water jet energy applied during hydraulic needling treatment will affect the depth of staple fiber penetration into the unbonded flash spun web and ultimately the ability of the spunlaced nonwoven fabric's permeability to be increased after thermal bonding. Although even a slight degree of staple fiber penetration will prevent quills from perculating through the resulting unbonded, spunlaced nonwoven fabric when used in barrier liner applications, the depth of penetration is important for high permeability filtration applications. It has been determined that slight penetration of the staple fibers will allow the permeability to be increased only slightly after thermal bonding. However, very deep penetration of the staple fibers will allow permeability to be increased to a large extent after thermal bonding. Therefore, in addition to the

thermal bonding level used, the amount of water jet energy employed during hydraulic needling can be varied (see Figs. 1 and 2 below) to tailor the ultimate permeability of the thermally bonded, spunlaced nonwoven fabric.

Referring now to the figures, schematic diagrams are shown to illustrate typical hydraulic needling methods and equipment (Figs. 1 and 2) as well as suitable thermal bonding equipment (Fig. 3).

Fig. 1 illustrates an apparatus for continuous processing of the staple fiber web/unbonded flash spun web composite structure to convert it into a spunlaced nonwoven fabric. In particular, staple fibers 1 are doffed in an air stream 2 onto a conveyor 3 where it is lightly needled by a few consolidating water jets 4 to tack it down. The staple fiber web is then positioned against an unbonded flash spun web 5 on conveyor 6 to form a composite web structure 7. The composite web structure is then drawn around drum washer 8 where a series of drum water jets 9 hydraulically needle the staple fiber web into the unbonded flash spun web such that the staple fibers are embedded into and entangled with the unbonded flash spun web to form a spunlaced nonwoven fabric 10. Thereafter, excess water is removed from the spunlaced nonwoven fabric by squeeze rolls 11 and vacuum dewatering equipment 12. The dewatered spunlaced nonwoven fabric 13 is then dried and collected on a wind up roll (not shown) for transporting or storage.

Fig. 2 is the same as Fig. 1 except that a series of water jets 14 are also used to hydraulically needle the unbonded flash spun web side of the composite web structure on conveyor 6. In this manner, both sides of the composite web structure are struck by high pressure water jets during the treatment process.

Fig. 3 illustrates a palmer roll bonder which is optionally used on the unbonded, spunlaced nonwoven fabric 13 of Figs. 1 or 2. (It will be understood that other bonding techniques or equipment may be appropriately used and that using a palmer roll bonder is not critical to the

invention). If the unbonded, spunlaced nonwoven fabric 13 is to be thermally bonded, it is unwound and fed to a palmer bonder 19 where it is wrapped around a 60 inch diameter heated drum 21 by conveyor blanket 22. Conveyor blanket 22 also helps to reduce shrinkage by applying pressure to the fabric as it is thermally bonded. Drum 21 thermally bonds the fabric by being heated to a temperature above the fusing point of the strands making up the flash spun web. Thereafter, the fabric is wrapped around a 24 inch chilled roll 23 to cool the fabric after thermal bonding. This is to prevent fabric shrinkage and edge curling. Thereafter, the thermally bonded, spunlaced nonwoven fabric 24 is collected on a wind up roll (not shown) for transporting or storage.

EXAMPLES

In the non-limiting Examples which follow, the following test methods were employed to determine various reported characteristics and properties. ASTM refers to the American Society of Testing Materials. TAPPI refers to the Technical Association of the Pulp and Paper Industry.

Basis weight was determined by ASTM D-3776-85 and is reported in oz/yd². Strip tensile strength was determined by ASTM D 1117 and is reported in lbs/linear inch. Frazier porosity was determined by ASTM D737-75 and is reported in ft³/ft²/min. Opacity was determined by TAPPI T-245 M-60 and is reported as a percentage.

Gurley Hill Porosity was determined by ASTM D-726-84 and is reported in second/100 cc.

Pore size was determined using a Coulter Porometer commercially available from Coulter Electronics Limited, Luton Beds., England. The sample to be analyzed was thoroughly wetted so that all accessible pores were completely filled with liquid. The wetted sample was then placed in the sample body of the filter holder assembly, secured with a locking ring and the pore size value was

recorded. Values are reported in microns for the maximum, minimum and mena pore size distribution.

Surface Area (SA) was determined by using a Strohlein
5 instrument which measures a 3 gram sample for single point BET nitrogen absorption. It is reported in m²/g.

Mullen Burst was determined by TAPPI T403-85 and is reported in psi.

10 Example 1

In this example, several samples were made by the inventive process using different sets of conditions. In all samples, 2 consolidation jets were used to tack down
15 loose fibers.

In sample 1, a pre-formed scrim of hydroentangled staple fibers was hydraulically needled into an unbonded T-800 "TYVEK" web using only belt washer jets (drum washer jets were turned off). Thus, this sample was prepared
20 without loose staple fibers. The squeeze rolls were left open.

In sample 2, a staple fiber web was hydraulically needled into an unbonded T-800 "TYVEK" web using a series of drum washer jets but no belt washer jets. In this
25 sample, 5 jets (5/20, 5/20, 5/40, 5/40, 5/40 jets) were used at 2500, 2300, 2000, 2100 and 2000 psi respectively. The squeeze rolls were left open.

In sample 3, the same conditions were followed as in sample 2 except that the squeeze rolls were closed.

30 In sample 4, the same conditions were followed as in sample 2 except that the type of water jets were altered. In this sample, 6 jets (5/20, 7/10, 5/20, 5/40, 5/40 and 5/40 jets) were used at 2500, 0, 2500, 2450, 2400 and 2500 psi respectively. The squeeze rolls were left open.

35

In sample 5, the sample conditions were followed as in sample 2 except that the type of water jets were altered. In this sample, 2 jets (5/20 and 5/40 jets) were used at 1200 and 1500 psi respectively. The squeeze rolls were closed.

The samples were tested for various physical properties while unbonded (U) and after thermal bonding (B) at 58 psi at 100 ft/min in a palmer roll bonder.

TABLE 1

Sample	U	B	U	B	U	B	U	B	U	B
	<u>1</u>		<u>2</u>		<u>3</u>		<u>4</u>		<u>5</u>	
Basis Weight	2.6	2.8	2.8	3.2	2.7	3.0	2.6	2.8	2.3	2.5
Thickness (mils)	18.8	13.7	20.6	13.6	12.0	12.5	19.9	13.2	10.4	11.2
Frazier Porosity	12.6	8.5	11.3	17.7	2.1	14.6	12.2	15.2	0.9	4.1
Opacity	95.7	76.6	93.5	85.9	93.8	75.9	92.1	80.7	96.9	78.8

Table 1 demonstrates that the Frazier porosity unexpectedly increases during thermal bonding of samples 2-4 where the staple fibers are deeply embedded in the unbonded T-800 "TYVEK" web whereas the pores of the unbonded T-800 "TYVEK" web close up during thermal bonding of sample 1 (i.e., Frazier porosity decreases) where the less mobile fibers of the pre-formed scrim penetrate only the surface layers of the unbonded T-800 "TYVEK" web. Sample 5 demonstrates that Frazier porosity can be controlled (i.e., tailored) by varying the amount of water jet energy during hydraulic needling. In this case, lower water jet energy causes less penetration of staple fibers into the unbonded T-800 "TYVEK" web and a smaller increase in Frazier porosity following thermal bonding.

In addition, sample 3 shows that even if the spunlaced fabric is consolidated (i.e., squeeze rolls closed) such that a low Frazier porosity exists in the unbonded state, the Frazier porosity can still be significantly increased with adequate thermal bonding.

Example 2

In this example, the inventive process was followed with the following modifications. Eight (8) spunlaced fabric samples were made from unbonded T-800 "TYVEK" and staple fibers using various staple fiber types and weights. They were as follows:

- Sample A = 0.9 oz/yd² 1.35 dpf polyester fiber/1.56 oz/yd² T-800 "TYVEK" web
Sample B = 0.9 oz/yd² splittable ribbon X-section acrylic fiber/1.56 oz/yd² T-800 "TYVEK" web
Sample C = 0.85 oz/yd² splittable polyester fiber/1.56 oz/yd² T-800 "TYVEK" web
Sample D = 0.9 oz/yd² 2.5 dpf ribbon X-section polyester fiber/1.56 oz/yd² T-800 "TYVEK" web
Sample E = 1.4 oz/yd² 3 dpf polyester fiber/1.56 oz/yd² T-800 "TYVEK" web
Sample F = 2.2 oz/yd² 6 dpf bicomponent (side-by-side) polyester fiber/1.56 oz/yd² T-800 "TYVEK" web
Sample G = 2.0 oz/yd² 1.35 dpf polyester fiber/1.56 oz/yd² T-800 "TYVEK" web
Sample H = 1.0 oz/yd² wetlaid woodpulp (60 wt.%) and 1.5 dpf polyester (40 wt.%) / 1.56 oz/yd² T-800 "TYVEK" web

Samples C & D contain fibers that split during hydroentangling. Denier per filament of the split fibers range from 0.2 to 2.5 dpf.

In Table 2, physical properties are reported for
unbonded, spunlaced nonwoven fabrics according to the
invention.

TABLE 2

Sample	A	B	C	D	E	F	G	H
Basis								
Weight	2.71	2.51	4.32	2.47	2.86	3.74	3.89	2.77
Thickness	20.20	20.57	17.13	20.75	21.49	29.09	30.52	21.91
(mils)								
Frazier								
Porosity	10.93	10.09	9.54	13.98	14.63	10.12	9.85	11.35
Opacity	93.88	94.67	95.82	93.93	94.91	95.75	96.02	95.72
Surface								
Area	6.79	6.90	6.34	4.94	-	4.91	4.78	6.85

Table 3 shows the physical properties of samples A-H after they have been thermally bonded using 58 psi steam at a speed of 100 ft/min (i.e., thermally bonded, spunlaced nonwoven fabrics).

TABLE 3

Sample	A	B	C	D	E	F	G	H
10 Basis Weight	2.80	2.48	2.26	2.66	3.05	3.90	4.19	2.72
Thickness (mils)	16.44	14.60	12.93	15.81	19.53	22.59	23.98	23.11
Frazier Porosity	18.65	14.98	10.84	19.48	19.07	19.77	12.98	12.73
15 Opacity	84.15	85.52	86.32	89.00	87.10	85.42	90.76	93.07
Pore Size Dist. (MIN)	7.1	6.5	6.5	7.6	8.0	6.7	6.7	6.4
20 Pore Size Dist. (MAX)	35.0	32.5	31.1	43.5	47.8	37.2	29.7	31.5
Pore Size Dist. (MEAN)	11.5	10.7	10.0	11.3	13.4	11.2	10.9	10.0

Comparing Tables 2 and 3 demonstrates that thermal bonding can be used to tailor the Frazier porosity (i.e., maintain or increase) of the spunlaced fabric to a level well suited for filtration applications such as vacuum cleaner bags (i.e., 10-20 ft³/ft²/min).

Example 3

In this example, the effect of the level of thermal bonding is demonstrated. Samples 1-4 from Example 1 were thermally bonded at (1) 48 psi steam pressure at 100 ft/min and (2) 54 psi steam pressure at 100 ft/min. The physical properties of the resulting thermally bonded, spunlaced nonwoven fabrics are set forth in Table 4 below.

TABLE 4

5	Sample	48	54	48	54	48	54	48	54
		psi	psi	psi	psi	psi	psi	psi	psi
		<u>1</u>		<u>2</u>		<u>3</u>		<u>4</u>	
	Basis								
	Weight	2.9	--	3.0	2.9	2.7	2.8	2.8	2.6
10	Thickness	15.4	--	14.6	13.8	13.3	12.8	16.1	14.7
	(mils)								
	Frazier								
15	Porosity	10.7	--	9.2	11.3	5.5	11.6	9.8	12.5
	Opacity	94.3	--	92.9	88.1	91.3	84.1	94.1	89.8

When compared with Table 1 for physical properties while unbonded and at 58 psi steam pressure at 100 ft/min, it is clear that increasing the bonding level (i.e., temperature) will increase the Frazier porosity of the resulting thermally bonded, spunlaced nonwoven fabric according to the invention (samples 1-5).

25

Table 5 compares physical properties of a representative thermally bonded sample of the invention (sample A) with ranges of typical physical properties for samples of commercially available prior art filtration media.

30

35

TABLE 5

5	Sample					Paper Vacuum
		<u>A</u>	<u>"HYSURF"</u>	<u>MELT-BLOWN</u>	<u>"TYVEK"</u>	<u>Cleaner Bag</u>
	Frazier					
	Porosity	18.7	8-18	30-40	<0.1	24
10	Pore Size					
	Dist.(MIN)	7.1	5-7	8-9	3	10
	Pore Size					
	Dist.(MAX)	35.0	19-23	30-40	9-12	69
15	Pore Size					
	Dist.(MEAN)	11.5	9-12	14-17	4-6	19
	Mullen					
20	Burst	91.8	40	10-15	90-120	30

This comparative table illustrates the ability of the inventive sample to act as a suitable filtration media for such things as vacuum cleaner bags.

25 Although particular embodiments of the present invention have been described in the foregoing description, it will be understood by those skilled in the art that the invention is capable of numerous modifications, substitutions and rearrangements without departing from the
 30 spirit or essential attributes of the invention. Reference should be made to the appended claims, rather than to the foregoing specification, as indicating the scope of the invention.

35

CLAIMS:

1. A process for making a spunlaced nonwoven fabric
5 comprising the steps of:
 (a) positioning a web of staple fibers against an
unbonded flash spun web on a supporting screen to form a
composite web structure; and
 (b) hydraulically needling the staple fiber side of
10 the supported composite web structure such that the staple
fibers penetrate the flash spun web and are embedded into
and entangled with the unbonded flash spun web.
2. The process according to claim 1 wherein hydraulic
needling is performed using water jets operating at a
15 pressure of between 200 and 3,000 psi.
3. The process according to claim 1 wherein the flash
spun web is comprised of polyolefin plexifilaments.
4. The process according to claim 3 wherein the
polyolefin is selected from the group consisting of
20 polyethylene and polypropylene.
5. The process according to claim 1 wherein the staple
fibers are selected from the group consisting of polyester,
nylon, acrylics, aramids, woodpulp and mixtures thereof.
6. An unbonded composite nonwoven fabric produced by
25 the process of claim 1 wherein the fabric has a Frazier
porosity of at least 4 ft³/ft²/min.
7. The process of claim 1 further comprising the step
of thermally bonding the spunlaced nonwoven fabric to
maintain or increase the permeability of the fabric.
- 30 8. The process of claim 7 wherein the fabric has a
Frazier porosity of between 10 and 40 ft³/ft²/min.
9. A thermally bonded, spunlaced nonwoven fabric
produced by the process of claim 7 wherein the fabric has a
Frazier porosity of at least 4 ft³/ft²/min.

35

10. An unbonded, spunlaced nonwoven fabric comprised of an unbonded flash spun web having staple fibers embedded into and entangled therewith, the fabric having a Frazier porosity of at least 4 ft³/ft²/min.

11. A thermally bonded, spunlaced nonwoven fabric comprised of an unbonded flash spun web having staple fibers embedded into and entangled therewith, the fabric having a Frazier porosity of at least 4 ft³/ft²/min.

12. The thermally bonded, spunlaced nonwoven fabric of claim 11 wherein the fabric has a Frazier porosity of between 10 and 40 ft³/ft²/min.

13. A downproof and featherproof liner made from the unbonded, spunlaced nonwoven fabric of claim 10.

14. The unbonded, spunlaced nonwoven fabric of claim 10 wherein the fabric is used as a liner for pillows, sleeping bags, comforters or garments.

15. A filtration media made from the thermally bonded, spunlaced nonwoven fabric of claim 11.

16. A vacuum cleaner bag made from the thermally bonded, spunlaced nonwoven fabric of claim 11.

FIG. 1






FIG. 2





INTERNATIONAL SEARCH REPORT

Internat'l Application No
PCT/US 93/10437

A. CLASSIFICATION OF SUBJECT MATTER

IPC 5 D04H13/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 5 D04H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y A	EP,A,0 365 293 (E.I.DU PONT DE NEMOURS) 25 April 1990 see the whole document ---	1,7 3,4,6, 8-11
Y A	EP,A,0 092 819 (ASAHI) 2 November 1983 see abstract; claims 1-8 ---	1,7 2,4
A	EP,A,0 108 621 (E.I.DU PONT DE NEMOURS) 16 May 1984 see abstract; claims 1-9; figures ---	1,2,4
A	EP,A,0 473 325 (E.I.DU PONT DE NEMOURS) 4 March 1992 cited in the application see the whole document ---	1-4,6
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- * "A" document defining the general state of the art which is not considered to be of particular relevance
- * "E" earlier document but published on or after the international filing date
- * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- * "O" document referring to an oral disclosure, use, exhibition or other means
- * "P" document published prior to the international filing date but later than the priority date claimed

- * "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- * "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- * "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * "&" document member of the same patent family

Date of the actual completion of the international search

8 February 1994

Date of mailing of the international search report

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Durand, F

INTERNATIONAL SEARCH REPORT

Intern al Application No
PCT/US 93/10437

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A,4 190 695 (DONALD O. NIEDERBAUER) 26 February 1980 see claims 1-8 -----	1,2

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 93/10437

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0365293	25-04-90	US-A- 4910075	20-03-90
		US-A- 4920001	24-04-90
		CA-A- 2000974	18-04-90
		JP-A- 3027167	05-02-91
EP-A-0092819	02-11-83	JP-C- 1702704	14-10-92
		JP-B- 3072322	18-11-91
		JP-A- 58186412	31-10-83
		JP-C- 1702706	14-10-92
		JP-B- 3072323	18-11-91
		JP-A- 59010319	19-01-84
		JP-A- 59010320	19-01-84
		US-A- 4548628	22-10-85
EP-A-0108621	16-05-84	US-A- 4442161	10-04-84
		AU-B- 556706	13-11-86
		AU-A- 2085283	10-05-84
		CA-A- 1247346	27-12-88
		JP-C- 1714950	27-11-92
		JP-B- 3073665	22-11-91
		JP-A- 59094659	31-05-84
EP-A-0473325	04-03-92	US-A- 5023130	11-06-91
		AU-B- 639128	15-07-93
		AU-A- 8179091	20-02-92
		CA-A- 2049161	15-02-92
US-A-4190695	26-02-80	CA-A- 1123589	18-05-82
		DE-A, C 2948329	26-06-80
		FR-A, B 2442907	27-06-80
		GB-A, B 2038714	30-07-80
		JP-B- 1026863	25-05-89
		JP-C- 1547443	28-02-90
		JP-A- 55074860	05-06-80

